

ASCOM 30

DESCRIPTION & APPLICATIONS

ASCOM limestone powder is the highest whiteness and high purity with low iron, silica and magnesium levels. Limestone is derived from enormous reserves.

Filler in the following industries:
Water - based decorative paints
powder coating (semi- gloss finish)
rubber moldings, paints, adhesives
and sealants.

Standard Packaging:

25 kg bag or
Jumbo bag

Physical Properties (typical)

Whiteness:	>97.0%
Brightness Ry (DIN 53163)	>95.5%
Density	2.7g/ml
Refractive Index	1.59
Mohs Hardness	3
pH (ISO 787/9)	9 Max.
Oil absorption (ISO 787/5)	18 ± 0.5g/100g
Moisture	0.2% Max
Loose Bulk Density	0.72 ± 0.05 gm/cm ³
DOP absorption	31.4± 0.5g/100g

Chemical Analysis (typical)

CaCO ₃	99.18%
CaO	55.91%
SiO ₂	0.09%
Al ₂ O ₃	0.04%
Fe ₂ O ₃	0.01%
MgO	0.05%
HCl Insoluble content	0.2% Max
L.O.I	43.64%

General Product Data (typical)

Retained on sieve 45μ	0.05% Max
D ₉₇	17 ± 1μm
D ₅₀	4.25 ± 0.25μm
< 2μm	30±2%

The data in the Technical Data Sheet represents average values which are valid and reliable but not legally binding. ACCM disclaims any liability arising from damages or consequential loss. This Technical Data Sheet renders all previous versions invalid. (April 2024)

PARTICLE SIZE DISTRIBUTION (MALVERN)

